Table S1. Proximate and Ultimate analysis of biochar and feedstock

Feed Stock	Pyrolysis Condition		Proximate Analysis (wt%)				Ultimate Analysis							
	Temperature (°C)	Heating rate (°C/min)	Moisture	Ash	VM	FC	C	O*	H	N	–	O/C	H/C	Ref.
Cellulose	–	–	4.37	0.51	93	3.7	39.99	54.2	5.8	0.01	–	1.02	1.74	[1]
			–	–	–	–	41.36	52.11	6.49	0.02	0.01	0.94	1.88	[2]
			–	–	–	–	43.09	50.67	5.96	0.13	0.14	0.88	1.66	[3]
			–	–	–	–	43.36	49.97	6.67	–	–	0.86	1.85	[4]
			0.06	95.84	4.1	41.74	49.04	6.79	0.13	0.3	0.16	0.10	0.03	[5]
			5.5	–	89.2	5.3	42.06	46.38	6.06	–	–	0.83	1.73	[6]
			7.03	0.85	87.45	4.67	41.53	51.04	6.68	0.75	0	0.92	1.93	[7]
			4.94	0.04	90.37	4.65	41.85	45.75	6.35	1.06	0.004	0.82	1.82	[8]
			5.9	–	89.1	5	44.4	49.3	6.3	0	0	0.83	1.70	[9]
			–	95.5	4.5	42.7	51.02	6.2	0.03	0.05	0.15	0.09	0.01	[10]
			4.67	0.07	93.37	1.89	51.47	43.93	2.87	1.69	0.03	0.64	0.67	[11]
			–	–	–	–	42.96	50.74	6.3	–	–	0.89	1.76	[12]
			4.72	–	89.91	5.37	39.32	49.78	6.02	0.16	–	0.95	1.84	[13]
			4.67	0.07	93.37	1.89	41.66	52.2	5.71	0.41	0.02	0.94	1.64	[14]
			6.9	0.3	92.9	–	44.6	49	6.4	–	–	0.82	1.72	[15]
			3.31	–	94.65	2.04	43.08	46.71	6.4	0.5	–	0.81	1.78	[16]
			1.99	–	91.97	6.04	43.65	49.93	6.33	–	–	0.86	1.74	[17]
Hemicellulose	–	–	–	–	–	–	39.26	54.95	5.76	0.02	0.01	1.05	1.76	[2]
			–	–	–	–	43.77	5.36	5.91	0.05	0.02	0.09	1.62	[3]
			6.9	3	71.5	18.6	41.7	51.9	6.3	0.1	–	0.93	1.81	[9]
			1.8	76.8	21.4	41.6	52.65	5.7	0.02	0.03	0.14	0.08	0.00	[10]
			3.96	5.59	79.42	11.03	42.14	41.4	6.22	0.69	–	0.74	1.77	[16]
Xylan	–	–	–	–	–	–	67.85	56.59	5.4	0.16	–	0.63	0.96	[4]
			1.8	89.18	9.02	41.76	48.88	6.72	–	0.4	0.16	0.10	0.00	[5]
			14.23	3.14	66.62	16.01	37.21	39.49	5.86	0.02	0.009	0.80	1.89	[8]
			–	–	–	–	43.25	49.9	6.3	–	–	0.87	1.75	[12]
			0.91	x	91.02	8.07	39.03	53.19	6.35	0.06	0.46	1.02	1.95	[13]
			5.83	3.61	77.79	12.78	40.26	51.55	5.49	2.7	–	0.96	1.64	[14]
Lignin	–	–	10.86	1.71	98.7	0.8	49.53	46.07	4.39	0.01	–	0.70	1.06	[1]
			–	–	–	–	56.82	5.21	33.62	0.11	1.32	0.07	7.10	[2]

			–	–	–	–	43.71	41.12	4.53	0.04	4.24	0.71	1.24	[3]
			–	–	–	–	50.85	43.92	5.17	0.06	–	0.65	1.22	[4]
			6.41	56.35	37.24	52.11	40.04	4.84	0.05	2.96	0.09	0.09	0.01	[5]
			13.1	12.35	35.74	38.81	47.65	19.6	4.3	2.92	0.08	0.31	1.08	[6]
			7.03	0.85	87.45	4.67	41.53	51.04	6.68	0.75	0	0.92	1.93	[7]
			6.05	11.76	64.56	17.63	41.44	31.44	4.9	0.16	4.25	0.57	1.42	[8]
			15.7	14.8	46.4	23.1	63.8	29.3	5.3	0.1	1.4	0.34	1.00	[9]
			4.2	58.9	36.9	48.3	43.6	4.9	0.1	3.1	0.10	0.08	0.03	[10]
			3.38	3.62	60.35	32.65	61.35	31.78	5.05	1.13	0.69	0.39	0.99	[11]
			–	–	–	–	57.7	34	4.38	0.11	–	0.44	0.91	[12]
			5.9	0.27	60.07	33.77	58.7	27.6	5.6	0.13	1.73	0.35	1.14	[13]
			3.41	3.62	60.37	32.6	61.33	31.71	5.14	1.13	0.69	0.39	1.01	[14]
			3.42	3.85	67.23	25.5	61.81	23.57	5.63	1.72	0	0.29	1.09	[16]
			4.19	1.35	48.83	45.63	65.03	27.6	5.03	0.04	2.3	0.32	0.93	[17]
Wheat straw	–	–	8.51	5.28	66.33	19.88	44.31	48.57	6.76	0.37	–	0.82	1.83	This Study
	–	–	3.37	10.08	70.37	16.18	43.44	50.55	5.05	0.96	–	0.87	1.40	
	200	10	–	–	–	–	44.79	47.9	6.93	0.39	–	0.80	1.86	
	300	1	–	–	–	–	57.67	35.27	5.41	1.65	–	0.46	1.13	
	300	10	–	–	–	–	54.08	39.75	5.08	1.03	–	0.55	1.13	
	300	10	–	–	–	–	58.09	34.357	5.863	1.69	–	0.44	1.21	
	400	10	–	–	–	–	61.9	32.6	4.11	1.39	–	0.39	0.80	
	500	5	–	–	–	–	61.24	32.547	4.743	1.47	–	0.40	0.93	
	500	10	–	–	–	–	67.19	28.75	2.87	1.19	–	0.32	0.51	
	500	10	–	–	–	–	61.57	33.074	3.846	1.51	–	0.40	0.75	
	600	10	–	–	–	–	67.92	29.06	1.82	1.2	–	0.32	0.32	
	700	1	–	–	–	–	67.55	27.583	3.607	1.26	–	0.31	0.64	
	700	10	–	–	–	–	64.04	33.36	1.36	1.25	–	0.39	0.25	
	700	10	–	–	–	–	64.47	32.153	2.237	1.14	–	0.37	0.42	
	–	–	5.8	5.1	70.8	18.3	47.9	45.5	6.1	0.3	0.2	0.71	1.53	[9]
	–	–	–	–	–	–	43.2	39.4	5	0.61	0.11	0.68	1.39	[12]
	–	–	44.1	45	6	0.4	0.01	0.14	1.02	44.1	45			[18]
	450	–	64.8	23	3.1	0.8	0.1	0.05	0.35	64.8	23	0.38	42.00	
	–	–	43.9	49.3	5.92	0.73	0.11	0.13	1.12	43.9	49.3			[19]
	900	–	5.3	4.69	75.88	14.12	43.64	44.09	5.82	0.68	–	0.76	1.60	[20]
	–	–	3.67	12.13	26.65	57.55	67.87	13.46	2.97	3.02	–	0.15	0.53	
	–	–	5.1	10.9	69.4	30.6	44.9	37.6	5.9	0.69	0.15	0.63	1.58	[21]

	307	–	–	–	–	–	–	–	–	–	–	0.13	0.84	
	392	–	–	–	–	–	–	–	–	–	–	0.12	0.63	
	310	–	–	–	–	–	–	–	–	–	–	0.12	0.56	
	352	–	–	–	–	–	–	–	–	–	–	0.1	0.49	
	133	–	–	–	–	–	–	–	–	–	–	0.12	0.71	
	156	–	–	–	–	–	–	–	–	–	–	0.11	0.57	
	242	–	–	–	–	–	–	–	–	–	–	0.1	0.55	
	–	–	–	–	–	–	48.4	6.5	43.9	1	0.2	0.10	10.88	[22]
	400	–	–	–	–	–	–	–	–	–	–	0.82	0.24	[23]
	475	–	–	–	–	–	–	–	–	–	–	0.63	0.21	
	550	–	–	–	–	–	–	–	–	–	–	0.46	0.12	
	–	–	4.53	8.12	68.7	18.65	39.65	44.86	5.63	1.41	0.37	0.85	1.70	[24]
	450	2	–	–	–	–	41.7	48.4	8.2	1.5	0.2	0.87	2.36	[25]
	450	450	–	–	–	–	52.3	35.8	9.4	1.9	0.6	0.51	2.16	
	–	–	9.66	6.8	68.34	15.2	45.79	47.53	5.71	0.73	0.24	0.78	1.50	[26]
	–	–	–	0.89	–	–	58.57	34.96	5.76	0.34	0.37	0.45	1.18	[27]
	–	–	6.3	1.3	78.4	14	45.4	48.3	6.2	0.12	0.02	0.80	1.64	[28]
	400	5	1.97	5.2	36.27	56.56	71.28	22.73	4.85	0.59	0.55	0.24	0.82	
	475	5	6.18	7.35	22.5	63.97	74.86	20.54	3.92	0.55	0.13	0.21	0.63	
	550	5	6.31	8.25	18.62	69.03	83.1	12.9	3.22	0.61	0.17	0.12	0.46	
	-		12	–	–	40.48	53.18	5.94	0.4	–	0.15	0.08	0.09	[29]
	400	5	35	–	–	40.66	54.27	4.19	0.88	–	0.10	0.06	0.19	
	500	5	12	–	–	73.4	24.41	1.49	0.7	–	0.02	0.05	0.34	
	600	5	15	–	–	76.58	20.38	2.23	0.81	–	0.03	0.08	0.48	
	700	5	14	–	–	75.16	22.59	1.47	0.78	–	0.02	0.05	0.41	
	Gasification		–	–	–	–	48.2	6.3	–	–	–	–	–	
Wheat husk	–	–	4.37	6.98	69.12	19.53	40.78	43.55	6.29	2.09	0.31	0.80	1.85	[24]
Corn stover	–	–	8.12	5.17	67.63	19.09	41.42	52.07	6.16	1.21	–	0.94	1.78	This Study
	200	10	–	–	–	–	42.64	49.08	6.89	1.1	–	0.86	1.94	
	300	10	–	–	–	–	59.09	33.05	6.17	1.52	–	0.42	1.25	
	400	10	–	–	–	–	68.64	25.14	4.62	1.49	–	0.27	0.81	
	500	10	–	–	–	–	71.18	23.39	3.79	1.52	–	0.25	0.64	
	600	10	–	–	–	–	75.89	19.58	2.78	1.59	–	0.19	0.44	
	700	10	–	–	–	–	79.01	17.42	1.85	1.52	–	0.17	0.28	
	–	–	–	–	–	–	44.6	48.07	6	0.73	0.1	0.81	1.61	[31]
	–	–	4.47	7.75	75.55	12.23	28.85	66.14	8.27	0.4	0.06	1.72	3.44	

	600	–	–	–	–	–	45.14	12.96	1.86	0.44	–	0.22	0.49	[32]
	–	–	–	–	–	–	43.2	44.4	5.9	0.8	–	0.77	1.64	[33]
	–	–	7.27	2.5	80.3	9.93	44.4	49.12	5.6	0.43	0.45	0.83	1.51	[34]
	–	–	5.12	6.16	77.49	11.32	44.47	47.88	4.19	0.97	0.45	0.81	1.13	[35]
	–	–	5.2	5.16	73.83	20.22	48.09	40.59	5.48	0.63	–	0.63	1.37	[36]
	–	–	–	3.92	–	–	39.95	50.16	4.23	1.34	0.4	0.94	1.27	[37]
	–	–	3.75	5.62	79.64	10.99	40.49	52.09	5.25	1.04	1.13	0.96	1.56	[38]
	500	15	1.8	32.4	11.1	54.7	62.8	32.95	2.9	1.3	0.05	0.39	0.55	[39]
	500	Preheat	1	49.7	14.9	34.4	37.8	58.84	2.5	0.8	0.06	1.17	0.79	
	730	Preheat	1.9	54	5.5	38.5	38.5	59.41	1.3	0.7	0.09	1.16	0.41	
	-	–	–	28	–	–	33.25	62.43	3.91	0.41	–	1.41	1.41	[29]
	400	5	–	18	–	–	60.55	35.88	–	–	–	–	–	
	500	5	–	18	–	–	62.32	34.44	–	–	–	–	–	
	600	5	–	17	–	–	60.98	36.70	–	–	–	–	–	
	700	5	–	16	–	–	58.39	39.41	–	–	–	–	–	
	Gasification			21	–	–	–	57.57	1.77	–	–	–	–	
Corn stalk	–	–	7.4	2.1	88.8	9.1	40.1	52.55	5.2	2.1	0.05	0.98	1.56	[1]
Corncob	–	–	7.75	8.13	66.81	17.31	41.62	35.64	6.07	0.63	0.16	0.64	1.75	[6]
Pine wood	–	–	8.82	0.83	70.82	19.53	47.39	45.12	7.4	0.09	–	0.71	1.87	This Study
	–	–	3	0.76	80.25	16	49.34	44.36	6.213	0.09	–	0.67	1.51	
	200	–	–	–	–	–	48.14	44.01	7.77	0.08	–	0.69	1.94	
	300	1	–	–	–	–	63.89	27.48	8.332	0.3	–	0.32	1.56	
	300	10	–	–	–	–	62.09	31.89	5.94	0.08	–	0.39	1.15	
	300	10	–	–	–	–	63.06	28.21	8.507	0.22	–	0.34	1.62	
	400	10	–	–	–	–	76.32	19.02	4.51	0.15	–	0.19	0.71	
	500	5	–	–	–	–	82.82	8.78	8.151	0.25	–	0.08	1.18	
	500	10	–	–	–	–	81.02	15.39	3.39	0.21	–	0.14	0.50	
	500	10	–	–	–	–	82.41	11.64	5.642	0.31	–	0.11	0.82	
	600	10	–	–	–	–	72.83	24.59	2.42	0.16	–	0.25	0.40	
	700	1	–	–	–	–	89.62	4.96	4.946	0.47	–	0.04	0.66	
	700	10	–	–	–	–	77.79	20.75	1.3	0.16	–	0.20	0.20	
	700	10	–	–	–	–	87.85	9.01	2.65	0.49	–	0.08	0.36	
	–	–	7.9	2.68	71.39	18.03	45.73	36.76	6.5	0.23	0.2	0.60	1.71	[6]
	–	–	1.93	0.52	81.59	15.96	46.63	46.74	6.43	0.20	0	0.75	1.65	[7]
	–	–	9.43	2.85	72.64	15.08	44.4	38.29	4.91	0.2	0.1	0.65	1.33	[13]
	450	2	–	–	–	–	46.5	43	9.1	1.4	0.01	0.69	2.35	[25]

	450	450	–	–	–	–	54.4	34	9.6	1.3	0.4	0.47	2.12	
	–	–	–	–	–	–	50.1	46.6	6.5	0.1	0.1	0.70	1.56	[40]
	–	–	6.42	0.83	79.16	20	45.76	48.66	5.54	0.04	–	0.80	1.45	[41]
	–	–	5.62	0.38	81.4	12.6	46.9	47.3	5.49	0.31	–	0.76	1.40	[42]
	120	10	–	–	–	–	53.59	36.28	5.77	1.18	3.18	0.51	1.29	[43]
	190	10	–	–	–	–	53.91	38.01	4.03	1.6	2.45	0.53	0.90	
	250	10	–	–	–	–	62.28	30.08	3.69	1.85	2.1	0.36	0.71	
	380	10	–	–	–	–	69.72	22.39	3.71	1.98	2.2	0.24	0.64	
	–	–	–	0.34	–	–	47.14	45.46	6.52	0.44	0.1	0.72	1.66	[44]
	790	–	–	6.22	–	–	82.87	9.15	1.33	0.42	–	0.08	0.19	
	934	–	–	9.59	–	–	85.38	4.38	0.34	0.31	–	0.04	0.05	
	1078	–	–	15.75	–	–	81.56	1.37	0.96	0.35	–	0.01	0.14	
	–	–	6.5	0.83	79.16	20	45.76	48.66	5.54	0.04	–	0.80	1.45	[45]
	–	–	–	–	–	–	49.95	43.97	5.94	0.14	–	0.66	1.43	[46]
	–	–	–	–	–	–	45.17	48.11	5.7	1.02	–	0.80	1.51	[47]
	–	–	–	0.3	–	–	48.8	45	6	0.2	–	0.69	1.48	[48]
	300	–	–	4.5	–	–	63.9	30.4	5.4	0.3	–	0.36	1.01	
	400	–	–	7.9	–	–	70.7	25.5	3.4	0.4	–	0.27	0.58	
	500	–	–	7.7	–	–	90.5	6.4	2.5	0.6	–	0.05	0.33	
	700	–	–	2.2	–	–	79	15	3	0.2	0.6	0.14	0.46	[49]
	800	–	–	–	–	–	90	6.9	0.67	0.22	–	0.06	0.09	[50]
	–	–	–	–	–	–	48.9	42.5	6.2	0.1	0.1	0.65	1.52	[18]
	450	–	–	–	–	–	75.5	17	3.7	0.2	0.1	0.17	0.59	
Poplar Wood	–	–	3.81	0.86	80.91	14.43	46.27	51.542	2.118	0.07	–	0.84	0.55	This Study
	300	1	–	–	–	–	65.23	32.279	2.171	0.32	–	0.37	0.40	
	300	10	–	–	–	–	64.18	33.554	2.086	0.18	–	0.39	0.39	
	500	5	–	–	–	–	85.8	11.912	1.958	0.33	–	0.10	0.27	
	500	10	–	–	–	–	81.5	16.817	1.403	0.28	–	0.15	0.21	
	700	1	–	–	–	–	89.68	8.473	1.377	0.47	–	0.07	0.18	
	700	10	–	–	–	–	87.91	10.588	1.022	0.48	–	0.09	0.14	
	–	–	7.54	73.85	18.61	47.49	5.45	37.91	1.41	0.2	0.80	5.22	3.10	[51]
	–	–	–	0.69	–	–	58.73	34.7	6.04	0.1	0.43	0.44	1.23	[27]
	–	–	7.2	3.04	–	–	46	44.08	5.58	0.16	0.85	0.72	1.46	[52]
	–	–	12.59	4.3	79.2	16.5	45.47	47.58	6.45	0.48	–	0.78	1.70	[53]
	300	25	7.65	32.94	16.76	50.3	51.75	41.76	3.91	2.58	–	0.61	0.91	
	400	25	5.27	39.45	27.9	32.65	50.31	43.93	3.09	2.67	–	0.65	0.74	

	500	25	4.35	43.04	24.84	32.12	56.89	37.43	2.86	2.82	–	0.49	0.60	
	600	25	5.44	50.93	21.74	27.33	55.21	40.57	1.96	2.26	–	0.55	0.43	
	700	25	4.89	52.17	13.67	34.16	50.44	45.97	1.51	2.07	–	0.68	0.36	
	800	25	4.81	26.8	15.68	57.52	43.83	51.1	2.9	2.17	–	0.87	0.79	
	–	–	–	–	–	–	45	48.8	6.2	–	–	0.81	1.65	[30]
	–	–	–	–	–	–	49.8	44.7	6.3	0.5	0.4	0.67	1.52	[54]
	500	10	–	–	–	–	75.7	20.6	2.6	1	0.07	0.20	0.41	
	600	10	–	–	–	–	78.7	17.7	2.4	1.2	0.05	0.17	0.37	
	700	10	–	–	–	–	80.2	16.7	1.9	1.2	0.05	0.16	0.28	
	800	10	–	–	–	–	84.3	13	1.7	0.9	0.05	0.12	0.24	
	–	–	–	–	–	–	43.9	45.2	5.7	0.7	0.01	0.77	1.56	[55]
	–	–	–	1.92	77.52	20.56	43.61	47.68	5.91	0.91	–	0.82	1.63	[56]
	–	–	–	0.58	–	–	48.8	44.5	6.5	0.2	–	0.68	1.60	[57]
	400	–	–	–	–	–	36	57.2	6.5	0.3	–	1.19	2.17	
	450	–	–	–	–	–	39.9	54.2	5.6	0.3	–	1.02	1.68	
	500	–	–	–	–	–	40.2	52.8	6.8	0.3	–	0.99	2.03	
	550	–	–	–	–	–	40.5	53	6.1	0.4	–	0.98	1.81	
Poplar Leaf	–	–	15.69	68.74	15.57	41.77	4.42	36.75	1.11	0.26	0.88	6.24	3.01	[51]
Hinoki Saw Dust	–	–	11	1.3	97.4	1.3	55.94	36.74	7.07	0.24	0.01	0.49	1.52	[1]
Rice Sraw	–	–	5.8	20.4	79.6	0	48.25	43.91	6.59	1.23	0.05	0.68	1.64	
Rice husk	–	–	5.6	20.2	78.4	1.4	51.29	41.3	6.81	0.29	0.02	0.60	1.59	
Larch Bark	–	–	8.7	2.6	97.1	0.2	47.07	47.2	5.5	0.23	0.02	0.75	1.40	
Bagasse	–	–	3.78	2.69	86.37	10.94	48.9	44.71	5.79	0.6	0	0.69	1.42	
Palm Oil fiber	–	–	6.6	3.4	93	3.7	46.73	46.59	6.12	0.56	0.02	0.75	1.57	
Chinar Leaf	–	–	9.91	67.6	22.49	42.78	5.3	37.76	3.7	0.55	0.88	5.34	8.38	[51]
Chinese cabbage	–	–	2.91	76.49	20.6	47.32	5.75	42.45	1.39	0.18	0.90	5.54	2.90	
Orange peel	–	–	9.23	69.74	21.03	48.06	4.43	37.06	0.92	0.3	0.77	6.27	2.49	
Castor	–	–	0	100	0	71.88	9.97	11.67	0.18	0.3	0.16	0.88	0.22	[5]
Corn Starch	–	–	0.41	90.92	8.67	43.74	48.83	7.09	0	0.34	0.16	0.11	0.00	
Soy Protein	–	–	3.91	81.11	14.98	50.17	26.97	7.33	14.68	0.85	0.15	0.20	6.53	
Bagasse	–	–	5.48	2.84	77.83	13.85	46.28	38.87	6.32	0.21	x	0.63	1.64	[6]
Cotton-stalk	–	–	8.87	5.46	68.7	16.97	42.7	35.52	6.25	0.94	0.26	0.62	1.76	
Rice-straw	–	–	8.54	10.5	65.77	15.19	39.28	33.44	6.17	1.41	0.66	0.64	1.88	
Rice HusK	–	–	7.67	14.96	60.69	16.68	38.45	32.37	5.68	0.56	0.31	0.63	1.77	

Japanese cedar	–	–	5.8	0.3	78.1	15.8	51.3	42.3	6.1	0.2	0	0.62	1.43	[9]
Japanese cypress	–	–	7.9	0.2	78.7	13.2	51.5	42.2	6.2	0.1	0	0.61	1.44	
Japanese oak	–	–	8.1	0.4	77.3	14.2	49.5	44	6.2	0.4	0	0.67	1.50	
Wood Bark	–	–	8.3	1	66	24.7	54.7	39.2	5.7	0.5	0	0.54	1.25	
Rice straw	–	–	6.8	11.1	65.5	16.6	47.6	45.7	6.2	0.5	0.1	0.72	1.56	
Rice husk	–	–	8.7	18.4	58.4	14.5	48.9	44.5	6.2	0.3	0.1	0.68	1.52	
Switchgrass	–	–	–	–	–	–	46.62	42.27	5.74	0.18	0.3	0.68	1.48	[12]
Easter redcedar	–	–	–	–	–	–	51.07	40.95	5.97	0.37	0	0.60	1.40	
Rice Straw	–	–	12.42	14.1	61.05	12.43	30.26	36.85	5.53	0.62	0.22	0.91	2.19	[13]
Anthracite coal	–	–	0.97	8.81	4.24	85.98	94.23	1.04	2.93	1.36	0.44	0.01	0.37	[17]
Oat Straw	–	–	4.38	3.21	74.04	18.37	43.23	45.39	6.12	0.88	–	0.79	1.70	[20]
	900	–	4.93	11.22	20.78	63.08	66.42	20.28	2.34	1.26	–	0.23	0.42	
Flax Straw		–	4.75	1.12	74.8	19.32	46.76	43.53	6.34	1.11	–	0.70	1.63	
	900	–	2.83	4.55	18.23	74.4	71.73	17.99	2.8	2.32	–	0.19	0.47	
Barley Straw		–	2.69	4.38	75.64	17.28	44.83	42.43	6.25	0.93	–	0.71	1.67	
	900	–	2.26	5.52	23.14	69.09	72.61	16.44	3.09	1.73	–	0.17	0.51	
		–	5.8	8.1	71.2	28.8	44.5	40.4	5.8	1.09	0.17	0.68	1.56	[21]
	400	–	–	–	–	–	–	–	–	–	–			[23]
	475	–	–	–	–	–	–	–	–	–	–			
	550	–	–	–	–	–	–	–	–	–	–			
Coal		–	3.56	57.99	18.71	19.74	26.11	12.03	2.26	1.03	0.58	0.35	1.04	[24]
Timothy Grass	450	2	–	–	–	–	44.9	44.4	8.4	1.8	0.5	0.74	2.24	[25]
	450	450	–	–	–	–	49.2	38.4	9.3	2.2	0.9	0.59	2.27	
Ginkgo	–	–	–	0.74	–	–	59.34	33.16	6.04	0.81	0.65	0.42	1.22	[27]
Flax Straw	–	–	8.1	3.1	79.9	8.9	47.8	45.7	6.4	0.07	0.01	0.72	1.61	[28]
	400	5	8.3	8.93	38.09	48.37	71.15	22.58	5.02	1.16	0.09	0.24	0.85	
	475	5	3.51	9.36	31.28	55.85	76.61	18	4.37	1.02	0	0.18	0.68	
	550	5	5.67	10.64	19.42	64.27	82.56	12.71	3.72	0.98	0.02	0.12	0.54	
Switch Grass	600	–	–	–	–	–	43.65	24.99	3.71	0.78		0.43	1.02	[32]
Switch Grass	500	–	0.9	52.5	7.1	39.5	39.4	58.60	1.3	0.7	0.002	1.12	0.40	[39]
	500	–	2.7	54.6	16.4	26.4	38.7	57.99	2.5	0.6	0.21	1.12	0.78	
	760	–	2.5	53	10.3	34.3	42.8	54.63	1.6	0.8	0.17	0.96	0.45	

Acacia	−	−	3.72	3.9	76.51	19.59	41.47	52.15	5.15	1.23		0.94	1.49	[41]
jarrah	700	−	−	3.3	−	−	85.3	8.7	1.6	0.2	0.8	0.08	0.23	[49]
Hazelnut	−	−	9.44	1.45	−	−	48.3	41.67	6.25	1.5	0.83	0.65	1.55	[52]
Rapeseed Straw	-	−	4.93	4.2	84.4	11.4	36.45	55.11	7.98	0.48	−	1.13	2.63	[53]
	300	25	8.51	27.78	78.2	37.66	55.42	35.49	5.59	3.5	−	0.48	1.21	
	400	25	7.83	28.3	34.56	40.6	59.88	31.56	4.66	3.9	−	0.40	0.93	
	500	25	12.98	43.25	31.1	39.89	60.37	31.81	4.15	3.67	−	0.40	0.82	
	600	25	9.15	36.1	16.89	36.09	64.98	30.07	1.62	3.33	−	0.35	0.30	
	700	25	9.34	45.06	27.81	37.54	59.22	36.25	1.28	3.26	−	0.46	0.26	
	800	25	4.44	39.74	17.29	41.03	60.77	34.41	1.33	3.49	−	0.42	0.26	
Rice Husk	−	−	−	19.41	65.43	15.16	47.05	44.12	6.3	0.94	−	0.11	0.26	[56]

* Collected and summarized by Mu-Hsiang Hsieh for PhD thesis.

REFERENCE

[1] A. Gani and I. Naruse, “Effect of cellulose and lignin content on pyrolysis and combustion characteristics for several types of biomass,” *Renew. Energy*, vol. 32, no. 4, pp. 649–661, 2007, doi: 10.1016/j.renene.2006.02.017.

[2] D. Chen, A. Gao, K. Cen, J. Zhang, X. Cao, and Z. Ma, “Investigation of biomass torrefaction based on three major components: Hemicellulose, cellulose, and lignin,” *Energy Convers. Manag.*, vol. 169, no. April, pp. 228–237, 2018, doi: 10.1016/j.enconman.2018.05.063.

[3] J. Y. Yeo, B. L. F. Chin, J. K. Tan, and Y. S. Loh, “Comparative studies on the pyrolysis of cellulose, hemicellulose, and lignin based on combined kinetics,” *J. Energy Inst.*, vol. 92, no. 1, pp. 27–37, 2019, doi: 10.1016/j.joei.2017.12.003.

[4] Z. Lai, S. Li, Y. Zhang, Y. Li, and J. Mu, “Influence of urea formaldehyde resin on the pyrolysis of biomass components: Cellulose, hemicellulose, and lignin,” *BioResources*, vol. 13, no. 2, pp. 2218–2232, 2018, doi: 10.15376/biores.13.2.2218-2232.

[5] Y. Qiao *et al.*, “Thermal decomposition of castor oil, corn starch, soy protein, lignin, xylan, and cellulose during fast pyrolysis,” *Bioresour. Technol.*, vol. 278, pp. 287–295, 2019, doi: 10.1016/j.biortech.2019.01.102.

[6] D. Lv, M. Xu, X. Liu, Z. Zhan, Z. Li, and H. Yao, “Effect of cellulose, lignin, alkali and alkaline earth metallic species on biomass pyrolysis and gasification,” *Fuel Process. Technol.*, vol. 91, no. 8, pp. 903–909, 2010, doi: 10.1016/j.fuproc.2009.09.014.

[7] P. D. Muley, C. Henkel, K. K. Abdollahi, C. Marculescu, and D. Boldor, “A critical comparison of pyrolysis of cellulose, lignin, and pine sawdust using an induction heating reactor,” *Energy Convers. Manag.*, vol. 117, pp. 273–280, 2016, doi: 10.1016/j.enconman.2016.03.041.

[8] H. Yu, Z. Zhang, Z. Li, and D. Chen, “Characteristics of tar formation during cellulose, hemicellulose and lignin gasification,” *Fuel*, vol. 118, pp. 250–256, 2014, doi: 10.1016/j.fuel.2013.10.080.

[9] Y. OKUMURA, T. OKADA, and K. OKAZAKI, “Effect of Cellulose, Hemi-cellulose and Lignin Compositions in Woody and Grass Biomass on Pyrolysis Process,” *J. High Temp. Soc.*, vol. 34, no. 4, pp. 160–165, 2008, doi: 10.7791/jhts.34.160.

[10] H. Yang *et al.*, “Vapor–solid interaction among cellulose, hemicellulose and lignin,” *Fuel*, vol. 263, no. September, p. 116681, 2020, doi: 10.1016/j.fuel.2019.116681.

[11] W. Guo, B. Zhang, J. Zhang, Z. Wu, Y. Li, and B. Yang, “Liquid chemical looping gasification of biomass: Thermodynamic analysis on cellulose,” *Chinese J. Chem. Eng.*, 2020, doi: 10.1016/j.cjche.2020.11.024.

[12] V. Pasangulapati, K. D. Ramachandriya, A. Kumar, M. R. Wilkins, C. L. Jones, and R. L. Huhnke, “Effects of cellulose, hemicellulose and lignin on thermochemical conversion characteristics of the selected biomass,” *Bioresour. Technol.*, vol. 114, pp. 663–669, 2012, doi: 10.1016/j.biortech.2012.03.036.

[13] H. Yu, Z. Wu, and G. Chen, “Catalytic gasification characteristics of cellulose, hemicellulose and lignin,” *Renew. Energy*, vol. 121, pp. 559–567, 2018, doi: 10.1016/j.renene.2018.01.047.

[14] C. Wu, Z. Wang, J. Huang, and P. T. Williams, “Pyrolysis/gasification of cellulose, hemicellulose and lignin for hydrogen production in the presence of various nickel-based catalysts,” *Fuel*, vol. 106, pp. 697–706, 2013, doi: 10.1016/j.fuel.2012.10.064.

[15] P. Rutkowski and A. Kubacki, “Influence of polystyrene addition to cellulose on chemical structure and properties of bio-oil obtained during pyrolysis,” *Energy Convers. Manag.*, vol. 47, no. 6, pp. 716–731, 2006, doi: 10.1016/j.enconman.2005.05.017.

[16] C. Zhao, E. Jiang, and A. Chen, “Volatile production from pyrolysis of cellulose, hemicellulose and lignin,” *J. Energy Inst.*, vol. 90, no. 6, pp. 902–913, 2017, doi: 10.1016/j.joei.2016.08.004.

[17] Z. Y. Du *et al.*, “Evolution properties of cellulose- and lignin-derived pyrolysis tars after interacting with coal chars,” *J. Anal. Appl. Pyrolysis*, vol. 122, pp. 332–341, 2016, doi: 10.1016/j.jaap.2016.09.008.

[18] S. Nanda, P. Mohanty, K. K. Pant, S. Naik, J. A. Kozinski, and A. K. Dalai, “Characterization of North American Lignocellulosic Biomass and Biochars in Terms of their Candidacy for Alternate Renewable Fuels,” *Bioenergy Res.*, vol. 6, no. 2, pp. 663–677, 2013, doi: 10.1007/s12155-012-9281-4.

[19] H. U. Lateef, M. Kazmi, A. N. Tabish, I. I. Cheema, and M. I. Rashid, “Effect of demineralization on physiochemical and thermal characteristics of wheat straw,” *Energy Sources, Part A Recover. Util. Environ. Eff.*, vol. 00, no. 00, pp. 1–10, 2020,

doi: 10.1080/15567036.2020.1791288.

[20] A. Aqsha, M. M. Tijani, B. Moghtaderi, and N. Mahinpey, “Catalytic pyrolysis of straw biomasses (wheat, flax, oat and barley) and the comparison of their product yields,” *J. Anal. Appl. Pyrolysis*, vol. 125, no. March, pp. 201–208, 2017, doi: 10.1016/j.jaap.2017.03.022.

[21] S. K. Satpathy, L. G. Tabil, V. Meda, S. N. Naik, and R. Prasad, “Torrefaction of wheat and barley straw after microwave heating,” *Fuel*, vol. 124, pp. 269–278, 2014, doi: 10.1016/j.fuel.2014.01.102.

[22] M. T. Reza, J. Mumme, and A. Ebert, “Characterization of hydrochar obtained from hydrothermal carbonization of wheat straw digestate,” *Biomass Convers. Biorefinery*, vol. 5, no. 4, pp. 425–435, 2015, doi: 10.1007/s13399-015-0163-9.

[23] R. Azargohar, S. Nanda, J. A. Kozinski, A. K. Dalai, and R. Sutarto, “Effects of temperature on the physicochemical characteristics of fast pyrolysis bio-chars derived from Canadian waste biomass,” *Fuel*, vol. 125, pp. 90–100, 2014, doi: 10.1016/j.fuel.2014.01.083.

[24] P. Kumar and B. Kumar Nandi, “Combustion characteristics of high ash Indian coal, wheat straw, wheat husk and their blends,” *Mater. Sci. Energy Technol.*, vol. 4, pp. 274–281, 2021, doi: 10.1016/j.mset.2021.08.001.

[25] S. Nanda, P. Mohanty, J. A. Kozinski, and A. K. Dalai, “Physico-Chemical Properties of Bio-Oils from Pyrolysis of Lignocellulosic Biomass with High and Slow Heating Rate,” *Energy Environ. Res.*, vol. 4, no. 3, 2014, doi: 10.5539/eer.v4n3p21.

[26] M. Z. Farooq, M. Zeeshan, S. Iqbal, N. Ahmed, and S. A. Y. Shah, “Influence of waste tire addition on wheat straw pyrolysis yield and oil quality,” *Energy*, vol. 144, pp. 200–206, 2018, doi: 10.1016/j.energy.2017.12.026.

[27] L. Wang *et al.*, “Comparative study of the fast pyrolysis behavior of ginkgo, poplar, and wheat straw lignin at different temperatures,” *Ind. Crops Prod.*, vol. 122, no. June, pp. 465–472, 2018, doi: 10.1016/j.indcrop.2018.06.038.

[28] R. Azargohar, K. L. Jacobson, E. E. Powell, and A. K. Dalai, “Evaluation of properties of fast pyrolysis products obtained, from Canadian waste biomass,” *J. Anal. Appl. Pyrolysis*, vol. 104, pp. 330–340, 2013, doi: 10.1016/j.jaap.2013.06.016.

[29] S. C. Peterson and M. A. Jackson, “Simplifying pyrolysis: Using gasification to produce corn stover and wheat straw biochar for sorptive and horticultural media,” *Ind. Crops Prod.*, vol. 53, pp. 228–235, 2014, doi: 10.1016/j.indcrop.2013.12.028.

[30] B. Szabó *et al.*, “Liquid phase pyrolysis of wheat straw and poplar in hexadecane solvent,” *J. Anal. Appl. Pyrolysis*, vol. 137, no. October, pp. 237–245, 2019, doi: 10.1016/j.jaap.2018.11.032.

[31] J. A. Conesa, A. Urueña, and D. Díez, “Corn stover thermal decomposition in pyrolytic and oxidant atmosphere,” *J. Anal. Appl. Pyrolysis*, vol. 106, pp. 132–137, 2014, doi: 10.1016/j.jaap.2014.01.010.

[32] S. C. Peterson, M. Appell, M. A. Jackson, and A. A. Boateng, “Comparing Corn Stover and Switchgrass Biochar:

Characterization and Sorption Properties," *J. Agric. Sci.*, vol. 5, no. 1, pp. 1–8, 2012, doi: 10.5539/jas.v5n1p1.

[33] Y. Li *et al.*, "Evaluating methane production from anaerobic mono- and co-digestion of kitchen waste, corn stover, and chicken manure," *Energy and Fuels*, vol. 27, no. 4, pp. 2085–2091, 2013, doi: 10.1021/ef400117f.

[34] M. Azuara, B. Baguer, J. I. Villacampa, N. Hedin, and J. J. Manyà, "Influence of pressure and temperature on key physicochemical properties of corn stover-derived biochar," *Fuel*, vol. 186, pp. 525–533, 2016, doi: 10.1016/j.fuel.2016.08.088.

[35] A. E. M. Fodah, M. K. Ghosal, and D. Behera, "Quality assessment of bio-oil and biochar from microwave-assisted pyrolysis of corn stover using different adsorbents," *J. Energy Inst.*, vol. 98, no. June, pp. 63–76, 2021, doi: 10.1016/j.joei.2021.06.008.

[36] N. Ali, M. Ashraf, K. Shahzad, M. Saleem, and A. Chughtai, "Fluidized bed fast pyrolysis of corn stover: Effects of fluidizing gas flow rate and composition," *Energy Sources, Part A Recover. Util. Environ. Eff.*, vol. 00, no. 00, pp. 1–13, 2019, doi: 10.1080/15567036.2019.1694105.

[37] D. Zhang, F. Wang, W. Yi, Z. Li, X. Shen, and W. Niu, "Comparison study on pyrolysis characteristics and kinetics of corn stover and its digestate by TG-FTIR," *BioResources*, vol. 12, no. 4, pp. 8240–8254, 2017, doi: 10.15376/biores.12.4.8240-8254.

[38] F. Meng, D. Wang, and M. Zhang, "Effects of different pretreatment methods on biochar properties from pyrolysis of corn stover," *J. Energy Inst.*, vol. 98, no. June, pp. 294–302, 2021, doi: 10.1016/j.joei.2021.07.008.

[39] P. Parthasarathy and S. K. Narayanan, "Characterization of Biochar from Fast Pyrolysis and Gasification Systems," *Environ. Prog. Sustain. Energy*, vol. 33, no. 3, pp. 676–680, 2014, doi: 10.1002/ep.

[40] O. F. H. Mongolian and P. Wood, "Influence of Steam Pressure on Chemical Changes of Heat-Treated Mongolian Pine Wood," *BioResources*, vol. 6, no. 2, pp. 1880–1889, 2011, doi: 10.15376/biores.6.2.1880-1889.

[41] G. Charis, G. Danha, and E. Muzenda, "Characterizations of biomasses for subsequent thermochemical conversion: A comparative study of pine sawdust and acacia tortilis," *Processes*, vol. 8, no. 5, 2020, doi: 10.3390/PR8050546.

[42] J. A. Onwudili and P. T. Williams, "Enhanced methane and hydrogen yields from catalytic supercritical water gasification of pine wood sawdust via pre-processing in subcritical water," *RSC Adv.*, vol. 3, no. 30, pp. 12432–12442, 2013, doi: 10.1039/c3ra41362d.

[43] S. Dawood, T. Sen, and C. M. Phan, "Effect of phosphoric acid and temperature profile on pine cone based activated carbon production and its effectiveness in the removal of Congo red dye by adsorption .," no. July 2014, 2013.

[44] N. Abdoulmoumine, A. Kulkarni, and S. Adhikari, "Effects of temperature and equivalence ratio on mass balance and energy analysis in loblolly pine oxygen gasification," *Energy Sci. Eng.*, vol. 4, no. 4, pp. 256–268, 2016, doi: 10.1002/ese3.124.

[45] G. Charis, G. Danha, E. Muzenda, and B. Patel, "Exploring the Valorization Potential of Pine Residues for Energy Applications

through Pyrolysis," *Int. J. Mater. Mech. Manuf.*, vol. 8, no. 2, pp. 46–49, 2020, doi: 10.18178/ijmmm.2020.8.2.482.

[46] S. Ramos-Carmona, J. F. Pérez, M. R. Pelaez-Samaniego, R. Barrera, and M. Garcia-Perez, "Effect of torrefaction temperature on properties of patula pine," *Maderas Cienc. y Tecnol.*, vol. 19, no. 1, pp. 39–50, 2017, doi: 10.4067/S0718-221X2017005000004.

[47] S. Biswas, H. Siddiqi, B. C. Meikap, T. K. Sen, and M. Khiadani, "Preparation and Characterization of Raw and Inorganic Acid-Activated Pine Cone Biochar and Its Application in the Removal of Aqueous-Phase Pb2+ Metal Ions by Adsorption," *Water. Air. Soil Pollut.*, vol. 231, no. 1, 2020, doi: 10.1007/s11270-019-4375-7.

[48] K. H. Kim, J. Y. Kim, T. S. Cho, and J. W. Choi, "Influence of pyrolysis temperature on physicochemical properties of biochar obtained from the fast pyrolysis of pitch pine (Pinus rigida)," *Bioresour. Technol.*, vol. 118, pp. 158–162, 2012, doi: 10.1016/j.biortech.2012.04.094.

[49] S. Jiang *et al.*, "Characterization of hard- and softwood biochars pyrolyzed at high temperature," *Environ. Geochem. Health*, vol. 39, no. 2, pp. 403–415, 2017, doi: 10.1007/s10653-016-9873-6.

[50] M. J. Bentley and R. S. Summers, "Ash pretreatment of pine and biosolids produces biochars with enhanced capacity for organic micropollutant removal from surface water, wastewater, and stormwater," *Environ. Sci. Water Res. Technol.*, vol. 6, no. 3, pp. 635–644, 2020, doi: 10.1039/c9ew00862d.

[51] H. Zhou, Y. Long, A. Meng, Q. Li, and Y. Zhang, "The pyrolysis simulation of five biomass species by hemi-cellulose, cellulose and lignin based on thermogravimetric curves," *Thermochim. Acta*, vol. 566, pp. 36–43, 2013, doi: 10.1016/j.tca.2013.04.040.

[52] A. Aghaalikhani, E. Savuto, A. Di Carlo, and D. Borello, "Poplar from phytoremediation as a renewable energy source: Gasification properties and pollution analysis," *Energy Procedia*, vol. 142, pp. 924–931, 2017, doi: 10.1016/j.egypro.2017.12.148.

[53] C. Gheorghe-Bulmau, A. Volceanov, I. Stanciulescu, G. Ionescu, C. Marculescu, and M. Radoiu, "Production and properties assessment of biochars from rapeseed and poplar waste biomass for environmental applications in Romania," *Environ. Geochem. Health*, vol. 3, 2021, doi: 10.1007/s10653-021-01061-3.

[54] U. Tezcan Un and F. Ates, "Low-cost adsorbent prepared from poplar sawdust for removal of disperse orange 30 dye from aqueous solutions," *Int. J. Environ. Sci. Technol.*, vol. 16, no. 2, pp. 899–908, 2019, doi: 10.1007/s13762-018-1716-9.

[55] C. F. Carrozza, G. Papa, A. Citterio, R. Sebastiano, B. A. Simmons, and S. Singh, "One-pot bio-derived ionic liquid conversion followed by hydrogenolysis reaction for biomass valorization: A promising approach affecting the morphology and quality of lignin of switchgrass and poplar," *Bioresour. Technol.*, vol. 294, no. July, p. 122214, 2019, doi: 10.1016/j.biortech.2019.122214.

[56] Y. He *et al.*, "Comparative study of fast pyrolysis, hydropyrolysis and catalytic hydropyrolysis of poplar sawdust and rice husk

in a modified Py-GC/MS microreactor system: Insights into product distribution, quantum description and reaction mechanism," *Renew. Sustain. Energy Rev.*, vol. 119, no. November, p. 109604, 2020, doi: 10.1016/j.rser.2019.109604.

[57] K. H. Kim *et al.*, "Investigation of physicochemical properties of biooils produced from yellow poplar wood (Liriodendron tulipifera) at various temperatures and residence times," *J. Anal. Appl. Pyrolysis*, vol. 92, no. 1, pp. 2–9, 2011, doi: 10.1016/j.jaap.2011.04.002.